	Evanesce™	Evanesce™ Flow
Filler Content by Weight	82%	62%
Average Filler Particle Size	0.6µm	0.5µm
Shrinkage in water (>24 hrs)	2.0%	NA
Flexural Strength	140 MPa	125 MPa
Flexural Modulus	10.4 GPa	5600 MPa
Compressive Strength	340 MPa	280 MPa
Radiopacity	250% Al.	150% Al.
Surface Roughness	0.07µm	NA